

12

EUROPEAN PATENT APPLICATION

21 Application number: **87106294.9**

51 Int. Cl.⁴: **B 01 J 8/24, C 08 F 10/00,**
C 08 F 2/34

22 Date of filing: **23.03.83**

30 Priority: **24.03.82 US 361547**

43 Date of publication of application: **21.10.87**
Bulletin 87/43

84 Designated Contracting States: **AT BE CH DE FR GB IT LI**
NL SE

60 Publication number of the earlier application in
accordance with Art. 76 EPC: **0089691**

71 Applicant: **UNION CARBIDE CORPORATION, 39 Old**
Ridgebury Road, Danbury Connecticut 06817 (US)

72 Inventor: **Jenkins, John Mitchell, III, 1405 Village Drive,**
South Charleston West Virginia 25309 (US)
Inventor: **Jones, Russell Lawrence, 7000 Falconbridge**
Road, Chapel Hill North Carolina 27514 (US)
Inventor: **Jones, Thomas Michael, 1099 Hollyberry Lane,**
South Charleston West Virginia 25309 (US)
Inventor: **Beret, Samil, 38 Maraposa Court, Danville**
California 94526 (US)

74 Representative: **Weinhold, Peter, Dr. et al,**
Patentanwälte Dr. V. Schmied-Kowarzik Dipl.-Ing. G.
Dannenberg Dr. P. Weinhold Dr. D. Gudel Dipl.-Ing. S.
Schubert Dr. P. Barz Siegfriedstrasse 8,
D-8000 München 40 (DE)

54 **A method for controlling the temperature of a fluidized bed especially a process for producing polymers.**

57 A process is described for a method for controlling the temperature of a fluidized bed during the production of polymers in a fluidized bed reactor by an exothermic polymerization reaction, which comprises continuously introducing into the bed a stream of gas cooled to below the maximum desired temperature within said bed and simultaneously or separately introducing a stream of liquid into said reactor under conditions such that an essentially uniform two-phase mixture of said gas and liquid is introduced in said bed at a level below the region of maximum desired temperature within said reactor.

This invention also refers to a process for producing polymers from one or more monomers by an exothermic polymerization reaction in a fluidized bed reactor in which the way of operation mentioned above is performed.

EP 0 241 947 A2

This invention relates to a method for controlling the temperature of a fluidized bed. Expecially it is directed to a novel method for:

improving the space time yield of an exothermic polymerization reaction conducted in a fluidized bed reactor, by increasing the removal of the heat of polymerization from the reactor by cooling gases, continuously removed from the reactor, to a temperature below the dew point temperature of such gases and returning the resultant two phase fluid mixture into the reactor to maintain the temperature of the fluidized bed at the desired level.

The discovery of the fluidized bed process for the production of polymers provided a means for producing these diverse and widely used polymers with a drastic reduction in capital investment and a dramatic reduction in energy requirements as compared to then conventional processes. The present invention provides a means for even greater savings in energy and capital cost by affording a simple and efficient means for obtaining a substantial increase in production rate in a given size reactor over what was previously possible in a fluidized bed process.

The most common and perhaps universal means of heat removal employed in conventional fluidized bed reactor processes is by compression and cooling of the recycle gas stream at a point external to the reactor. In commercial scale fluidized bed reaction systems for producing polymers such as polyethylene, the amount of fluid which must be circulated to remove the heat of polymerization is greater than the amount of fluid required for support of the fluidized bed and for adequate solids mixing in the fluidized bed. The fluid velocity in the reactor is limited to prevent excessive entrainment of solids. A constant bed temperature will result

if the heat generated by the polymerization reaction (which is proportional to the polymer production rate) is equal to the heat absorbed by the fluidizing stream as it passes through the bed, plus any heat removed or lost by other means.

Unfortunately, it has long been believed that the recycle gas temperature could not be lowered any further than to a point slightly above the dew point of the recycle gas stream. The dew point is that temperature at which liquid condensate begins to form in the gas stream. Common practice has been to limit the temperature of the recycle stream at the outlet of the cycle heat exchange zone to a temperature at least about 3 to 10°C above its dew point (see copending U. S. patent application Ser. No. 49,555 of June 18, 1979, equivalent to published European Patent Specification No. 0 021 605, page 22, lines 8-22). This assumption was predicated on the belief that the introduction of liquid into a gas phase fluidized bed reactor would inevitably result in plugging of the distribution plate, if one is employed; non-uniformity of monomer concentrations inside the fluidized bed and accumulation of liquid at the bottom of the reactor which would interfere with continuous operation or result in complete reactor shut-down. For products, such as those using hexene as a comonomer, the relatively high dew point of the recycle stream has until now severely restricted the production rate.

The primary limitation on reaction rate in a fluidized bed reactor is the rate at which heat can be removed from the polymerization zone. Although they differ in very important ways from gas fluidized bed reaction systems, the same heat limitation problems exist in other types of reaction systems such as stirred reaction systems and to some extent, slurry reaction systems.

In U.S. Patent No. 3,256,263, heat removal in a stirred reaction system is achieved by the compression of

recycle gases and expansion upon reentry into the reactor. In other stirred or paddle-type reaction systems some additional cooling is effected by the injection of liquid onto the top of the bed. See for example U.S. Patents Nos. 3,254,070; 3,300,457 and 3,652,527.

In U.S. Patents Nos. 3,965,083; 3,970,611 and 3,971,768 assigned to Standard Oil Co., cooling of a stirred bed reactor is supplemented by injection of liquids on the top of the bed.

In U.S. Patent No. 4,012,573 (Treschman et al.) gases withdrawn from a stirred reactor are condensed to liquid and returned in liquid form to the stirred reactor where the liquid is brought into desired contact with polymer in the stirred bed.

Mitsubishi Petrochemical Co. has proposed the use of liquids or regasified liquids for cooling in a gas phase reactor (J55/045,744/80 and DT 2 139 182). In both of these descriptions the liquid or regasified liquid is injected into the bed rather than entering with the fluidizing gas as in the present invention. DT 2 139 182 is specific to stirred beds rather than fluidized beds. In J55/045,744/80 the liquid is regasified before being injected into the fluidized bed.

In a fluidized bed reaction system, as distinguished from stirred or paddle-type reaction systems, uniform distribution of monomer and catalysts in the upwardly moving gas stream is essential to avoid hot spots and resulting polymer chunks. In stirred and paddle-type reactors these problems are overcome by mechanical stirring and agitation. A further requirement of a fluidized bed reactor system is that the velocity of gas flowing through the reactor be adequate to maintain the bed in a fluidized state. The gas velocity required to keep the bed in a fluidized suspension cannot be achieved under normal conditions by mere injection of liquid

at the bottom of the bed. Therefore, the direct liquid injection cooling of a reactor, as described by Treschman et al. is not a viable option for a fluidized bed reaction system.

While not limited to any particular type or kind of polymerization reaction (so long as the reaction is of an exothermic nature), this invention is particularly suited to polymerization reactions involving the polymerization of one or more of the monomers listed below:

I. Olefin type: ethylene, propylene, butene-1, pentene-1, 4-methylpentene-1, hexene-1, styrene.

II. Polar vinyl monomer type: vinyl chloride, vinyl acetate, vinyl acrylate, methyl methacrylate, tetrafluoroethylene, vinyl ether, acrylonitrile.

III. Diene type (conjugated and non-conjugated): butadiene, 1,4-hexadiene, isoprene, ethylidene norbornene.

IV. Acetylene type: acetylene, substituted acetylene, such as methyl acetylene.

V. Aldehyde type: formaldehyde.

It is to be noted that catalysts employable in the fluidized bed polymerization of the above monomer types would, respectively, most usually be as follows:

I. Coordinated anionic catalyst

II. Cationic catalyst for copolymers with ethylene only; others of this type require a free-radical catalyst

III. Either a free-radical catalyst or a coordinated anionic catalyst

IV. A coordinated anionic catalyst

V. An anionic catalyst

Although this invention is not limited to any specific type of polymerization reaction, the following discussions of the operation of the process are directed to polymerizations of olefin-type monomers where the invention has been found to be especially advantageous.

In very general terms, a conventional fluidized bed process for producing resins, particularly polymers produced from monomers, is practiced by passing a gaseous stream containing one or more monomers continuously through a fluidized bed reactor under reactive conditions and in the presence of catalyst. The gaseous stream containing unreacted gaseous monomer is withdrawn from the reactor continuously, compressed, cooled and recycled into the reactor. Product is withdrawn from the reactor. Make-up monomer is added to the recycle stream.

The polymer-forming reaction is exothermic, making it necessary to maintain in some fashion the temperature of the gas stream inside the reactor at a temperature not only below the resin and catalyst degradation temperatures, but at a temperature below the fusion or sticking temperature of resin particles produced during the polymerization reaction. This is necessary to prevent plugging of the reactor due to rapid growth of polymer chunks which cannot be removed in a continuous fashion as product. It will be understood, therefore, that the amount of polymer that can be produced in a fluidized bed reactor of a given size in a specified time period is directly related to the amount of heat which can be withdrawn from the fluidized bed.

In accordance with this invention the recycle gas stream is intentionally cooled to a temperature below the dew point of the recycle gas stream to produce a two-phase gas-liquid mixture under conditions such that the liquid phase of said mixture will remain entrained in the gas phase of said mixture at least from the point of entry into the fluidized bed reactor until volatilized or until passage into the fluidized bed. A substantial increase in space time yield results from the practice of this invention with little or no change in product properties or quality. When practiced as described herein the overall process proceeds continuously and smoothly and without unusual operational difficulties.

It may be desirable in some instances to raise the dew point of the recycle gas stream to further increase heat removal. The recycle stream dew point can be increased by: (1) raising the operating pressure of the reaction system; (2) increasing the concentration of condensible fluids in the recycle stream; and/or (3) reducing the concentration of non-condensable gases in the recycle stream. In one embodiment of this invention, the dew point of the recycle stream may be increased by the addition of a condensible fluid to the recycle stream which is inert to the catalyst, reactants, and the products of the polymerization reaction. The fluid can be introduced into the recycle stream with the make-up fluid or by any other means or at any other point in the system. Examples of such fluids are saturated hydrocarbons, such as butanes, pentanes or hexanes.

A primary limitation on the extent to which the recycle gas stream can be cooled below the dew point is in the requirement that gas-to-liquid ratio be maintained at a level sufficient to keep the liquid phase of the two-phase fluid mixture in an entrained or suspended condition until the liquid is vaporized. It is also necessary that the velocity of the upwardly flowing fluid stream be sufficient to maintain the fluidized bed in a suspended condition.

While the liquid content of the two-phase recycle stream can be quite high, as a general rule, the quantity of condensed liquid contained in the gas phase should not exceed about 20 weight percent and preferably should not exceed about 10 weight percent, provided always that the velocity of the two-phase recycle stream is high enough to keep the liquid phase in suspension in the gas and to support the fluidized bed within the reactor.

The entry point for the two-phase recycle stream should be below the fluidized bed (polymerization zone) to ensure uniformity of the upwardly flowing gas stream and to

maintain the bed in a suspended condition. The recycle stream containing entrained liquid is introduced into the reactor at a point in the lower region of the reactor and most preferably at the very bottom of the reactor to ensure uniformity of the fluid stream passing upwardly through the fluidized bed.

A baffle or similar means for preventing regions of low gas velocity in the vicinity of the recycle stream entry point may be provided to keep solids and liquids entrained in the upwardly flowing recycle stream.

According to an embodiment of the present invention the two-phase mixture is divided into at least two separate streams at least one of which is introduced into the reactor, e.g. at a point below the fluidized bed and one or more of said streams is optionally introduced into said fluidized bed, provided that the velocity of all gases introduced below said fluidized bed is at least sufficient to support said bed and to maintain it in a fluidized condition. In all cases the composition of the gas stream is kept essentially uniform and flowing in a manner such that there are no dead spaces in the bed where unremovable solids can form.

It will be apparent that if desired, it is possible to form a two-phase fluid stream within the reactor at the point of injection by separately injecting gas and liquid under conditions which will produce a two-phase stream. Little advantage is seen in operating in this fashion due to the added and unnecessary burden and cost of separating the gas and liquid phases after cooling. It may however, be desirable to inject make-up monomer into the reactor in this fashion. The injection of liquid or gaseous make-up monomer at the point of entry of the two-phase recycle stream or elsewhere in the reactor or in the recycle stream is contemplated by this invention. In a special embodiment of this invention the additional quantities of one or more monomers added to replace monomers polymerized and withdrawn as product are introduced into the recycle stream prior to entry of the said two-phase mixture into the reactor.

The advantages of this invention are not limited to the production of polyolefin resins. This invention can be practiced in connection with any exothermic polymerization process carried out in a gas phase fluidized bed. The

0241947

advantages of this invention over conventional processes will generally increase in direct relation to the nearness of the dew point temperature of the recycle stream to the reaction temperature within the interior of the fluid bed. For obvious reasons this invention cannot be used in a reaction system in which the reaction temperature within its fluidized bed is below the dew point of the recycle gas stream.

The applicability of this invention to the production of any given polymer can be determined by the use of the following formula:

$$X = \frac{P \cdot H_{rxn}}{G_{mass} \cdot CP_{gas} (T_{rxn} - T_{limit})}$$

- P = desired polymer production rate; constrained to rates giving X less than 1.0 without subject invention.
- H_{rxn} = heat of polymerization of specific polymer being produced.
- G_{mass} = mass flow rate of recycle stream; limited to a minimum value by the need for adequate fluidization and mixing in the bed and to a maximum value by entrainment of solids. Specific minima and maxima depend on numerous factors known to those skilled in the art.
- CP_{gas} = heat capacity of the recycle stream.
- T_{rxn} = temperature of the reaction zone (fluid bed); has maximum value depending on the sticking temperature of the polymer at the pressure of the recycle stream and/or the catalyst

performance, and a minimum value which is dependent on catalyst performance.

T_{limit} = minimum temperature of the recycle stream entering the reaction zone as limited prior to the present invention. This temperature is either the dew point of the recycle stream or the cooling limit of the heat exchange zone, whichever is higher. If T_{limit} is the recycle stream dew point, the invention is practiced by simply cooling the stream to a temperature below its dew point. If T_{limit} is controlled by the heat exchange zone, the invention is practiced by adding a condensable fluid to increase the dew point of the recycle stream to a temperature above the cooling limit of the heat exchange zone.

Whenever the value of X is greater than 1, the use of this invention will afford a benefit and as the value of X increases, the greater are the benefits which can result from this invention.

A fluidized bed reaction system which is particularly suited to production of polyolefin resin by the practice of the process of the present invention is illustrated in the drawing. With reference thereto, the reactor 10 consists of a reaction zone 12 and a velocity reduction zone 14.

In general, the height to diameter ratio of the reaction zone can vary in the range of about 2.7:1 to about 4.6:1. The range, of course, can vary to larger or smaller ratios and depends upon the desired production capacity. The cross-sectional area of the velocity reduction zone 14 is typically within the range of about 2.6 to about 2.8 multiplied by the cross-sectional area of the reaction zone 12.

The reaction zone 12 includes a bed of growing polymer particles, formed polymer particles and a minor amount of catalyst particles fluidized by the continuous flow of polymerizable and modifying gaseous components in the form of make-up feed and recycle fluid through the reaction zone. To maintain a viable fluidized bed, the superficial gas velocity through the bed must exceed the minimum flow required for fluidization, and preferably is at least 6 cm/s (0.2 ft/sec) above minimum flow. Ordinarily, the superficial gas velocity does not exceed 1.5 m/s (5.0 ft/sec) and usually no more than 0.76 m/s (2.5 ft/sec) is sufficient.

It is essential that the bed always contain particles to prevent the formation of localized "hot spots" and to entrap and distribute the particulate catalyst throughout the reaction zone. On start up, the reactor is usually charged with a base of particulate polymer particles before gas flow is initiated. Such particles may be identical in nature to the polymer to be formed or different therefrom. When different, they are withdrawn with the desired formed polymer particles as the first product. Eventually, a fluidized bed of desired polymer particles supplants the start-up bed.

The partially or totally activated precursor composition and/or catalyst used in the fluidized bed is preferably stored for service in a reservoir 16 under a blanket of a gas which is inert to the stored material, such as nitrogen or argon.

Fluidization is achieved by a high rate of fluid recycle to and through the bed, typically in the order of about 50 times the rate of feed of make-up fluid. The fluidized bed has the general appearance of a dense mass of individually moving particles as created by the percolation of gas through the bed. The pressure drop through the bed is equal to or slightly greater than the weight of the bed divided by the cross-sectional area. It is thus dependent on the geometry of the reactor.

Make-up fluid is fed to the ^{recycle line} ~~bed~~ at point 18. The composition of the make-up stream is determined by a gas analyzer 21. The gas analyzer determines the composition of the recycle stream and the composition of the make-up stream is adjusted accordingly to maintain an essentially steady state gaseous composition within the reaction zone.

The gas analyzer is a conventional gas analyzer which operates in conventional manner to indicate recycle stream composition and which is adapted to regulate the feed and is commercially available from a wide variety of sources. Generally, the gas analyzer 21 can be positioned so as to receive gas from a point between the velocity reduction zone 14 and heat exchanger 24.

To ensure complete fluidization, the recycle stream and, where desired, part of the make-up stream are returned through recycle line 22 to the reactor at point 26 below the bed. There may be preferably a gas distributor plate 28 above the point of return to aid in fluidizing the bed. In passing through the bed, the recycle stream absorbs the heat of reaction generated by the polymerization reaction.

The portion of the fluidizing stream which does not react in the bed constitutes the recycle stream which is removed from the polymerization zone, preferably by passing it into velocity reduction zone 14 above the bed where entrained particles are given an opportunity to drop back into the bed.

The recycle stream is then compressed in a compressor 30 and then passed through a heat exchange zone wherein the heat of reaction is removed before it is returned to the bed. The heat exchange zone is typically a heat exchanger 24 which can be of the horizontal or vertical type. The recycle stream is then returned to the reactor at its base 26 and to the fluidized bed through gas distributor plate 28. A gas deflector 32 is preferably installed at the inlet to the reactor to prevent contained polymer particles from settling out and agglomerating into a solid mass.

The temperature of the bed is controlled at an essentially constant temperature under steady state conditions by constantly removing the heat of reaction. No noticeable temperature gradient appears to exist within the upper portion of the bed. A temperature gradient will exist in the bottom of the bed in a layer of about 15 to 30 cm (6 to 12 inches), between the temperature of the inlet fluid and the temperature of the remainder of the bed.

Good gas distribution plays an important role in the operation of the reactor. The fluidized bed contains growing and formed particulate polymer particles, as well as catalyst particles. As the polymer particles are hot and possibly active, they must be prevented from settling, for if a quiescent mass is allowed to exist, any active catalyst contained therein may continue to react and cause fusion. Diffusing recycle fluid through the bed at a rate sufficient to maintain fluidization through the bed is, therefore, important.

Gas distribution plate 28 is a preferred means for achieving good gas distribution and may be a screen, slotted plate, perforated plate, a plate of the bubble-cap type and the like. The elements of the plate may all be stationary, or the plate may be of the mobile type disclosed in U.S. 3,298,792. Whatever its design, it must diffuse the recycle fluid through the particles at the base of the bed to keep the bed in a fluidized condition, and also serve to support a quiescent bed of resin particles when the reactor is not in operation.

The preferred type gas distributor plate 28 is generally of the type which is fabricated from metal and which has holes distributed across its surface. The holes are normally of a diameter of about 1.3 cm (1/2 inch). The holes extend through the plate, and over each hole there is positioned a triangular angle iron identified as reference numeral 36 which

is fixedly mounted to plate 28. The angle irons serve to distribute the flow of fluid along the surface of the plate so as to avoid stagnant zones of solids. In addition they prevent the resin from flowing through the holes when the bed is settled.

Any fluid inert to the catalyst and reactants can also be present in the recycle stream. An activator compound, if utilized, is preferably added to the reaction system downstream from heat exchanger 24. Thus, the activator may be fed into the recycle system from dispenser 38 through line 40.

It is essential to operate the fluid-bed reactor at a temperature below the sintering temperature of the polymer particles to ensure that sintering will not occur. The sintering temperature is a function of resin density. In general, polyethylene low-density resins, for example, have a low sintering temperature and polyethylene high-density resins, for example, have a higher sintering temperature. For example, temperatures of from about 75°C to about 95°C are used to prepare ethylene copolymers having a density of from about 0.91 g/cm³ to about 0.95 g/cm³, while temperatures of from about 100°C to about 115°C are used to prepare ethylene copolymers or homopolymers having a density of from about 0.95 g/cm³ to about 0.97 g/cm³.

The fluid-bed reactor may be operated at pressures of up to about 6.9 MPa (1000 psi), and is for polyolefin resin production preferably operated at a pressure of from about 0.69 MPa (100 psi) to about 2.4 MPa (350 psi), with operation at the higher pressures in such ranges favoring heat transfer since an increase in pressure increases the unit volume heat capacity of the gas.

The partially or totally activated precursor composition and/or catalyst (hereinafter collectively referred to as catalyst) is injected into the bed at a rate equal to its consumption at a point 42 which is above distributor plate 28. Preferably, the catalyst is injected at a point in the

bed where good mixing of polymer particles occurs. Injecting the catalyst at a point above the distribution plate is an important feature for satisfactory operation of a fluidized bed polymerization reactor. Since catalysts are highly active, injection of the catalyst into the area below the distributor plate may cause polymerization to begin there and eventually cause plugging of the distributor plate. Injection into the fluidized bed, instead, aids in distributing the catalyst throughout the bed and tends to preclude the formation of localized spots of high catalyst concentration which may result in the formation of "hot spots." Injection of the catalyst into the reactor above the bed may result in excessive catalyst carryover into the recycle line where polymerization may begin and plugging of the line and heat exchanger may eventually occur.

The catalyst can be injected into the reactor by various techniques. It is preferred, however, to continuously feed the catalyst into the reactor utilizing a catalyst feeder as disclosed; e.g., in U.S. patent 3,779,712. The catalyst is preferably fed into the reactor at a point 20 to 40 percent of the reactor diameter away from the reactor wall and at a height of about 5 to about 30 percent of the height of the bed.

A gas which is inert to the catalyst, such as nitrogen or argon, is preferably used to carry the catalyst into the bed.

The rate of polymer production in the bed depends on the rate of catalyst injection and the concentration of monomer(s) in the recycle stream. The production rate is conveniently controlled by simply adjusting the rate of catalyst injection.

Since any change in the rate of catalyst injection will change the reaction rate and hence rate of generation of the heat of reaction, the temperature of the recycle stream entering the reactor is adjusted upwards and downwards to

accommodate any change in the rate of heat generation. This ensures the maintenance of an essentially constant temperature in the bed. Complete instrumentation of both the fluidized bed and the recycle stream cooling system is, of course, useful to detect any temperature change in the bed so as to enable either the operator or a conventional automatic control system to make a suitable adjustment in the temperature of the recycle stream.

Under a given set of operating conditions, the fluidized bed is maintained at essentially a constant height by withdrawing a portion of the bed as product at the rate of formation of the particulate polymer product. Since the rate of heat generation is directly related to the rate of product formation, a measurement of the temperature rise of the fluid across the reactor (the difference between inlet fluid temperature and exit fluid temperature) is indicative of the rate of particulate polymer formation at a constant fluid velocity if no vaporizable liquid is present in the inlet fluid.

On discharge of particulate polymer product from reactor 10, it is desirable and preferable to separate fluid from the product and to return the fluid to the recycle line 22. There are numerous ways known to the art to accomplish this. One preferred system is shown in the drawings. Thus, fluid and product leave reactor 10 at point 44 and enter product discharge tank 46 through valve 48 which is designed to have minimum restriction to flow when opened such as a ball valve. Positioned above and below product discharge tank 46 are conventional valves 50, 52 with the latter being adapted to provide passage of product into product surge tank 54. Product surge tank 54 has venting means illustrated by line 56 and gas entry means illustrated by line 58. Also positioned at the base of product surge tank 54, is a discharge valve 60 which when in the open position discharges product for

conveying to storage. Valve 50 when in the open position releases fluid to surge tank 62. Fluid from surge tank 62 is directed through a filter absorber 64 and thence through a compressor 66 and into recycle line 22 through line 68.

In a typical mode of operation, valve 48 is open and valves 50, 52 are in a closed position. Product and fluid enter product discharge tank 46. Valve 48 closes and the product is allowed to settle in product discharge tank 46. Valve 50 is then opened permitting fluid to flow from product discharge tank 46 to surge tank 62 from which it is continually compressed back into recycle line 22. Valve 50 is then closed and valve 52 is opened and any product in product discharge tank 46 flows into product surge tank 54. Valve 52 is then closed. The product is purged with inert gas, preferably nitrogen, which enters product surge tank 54 through line 58 and is vented through line 56. Product is then discharged from product surge tank 54 through valve 60 and conveyed through line 20 to storage.

The particular timing sequence of the valves is accomplished by the use of conventional programmable controllers which are well known in the art. Moreover, the valves can be kept substantially free of agglomerated particles by installation of provisions for directing a stream of gas periodically through the valves and back to the reactor.

Another preferred product discharge system which may be alternatively employed is that disclosed and claimed in the copending U. S. patent application of Robert G. Aronson filed July 28, 1981, Ser. No. 287815 and entitled Fluidized Bed Discharge System. Such a system employs at least one (parallel) pair of tanks comprising a settling tank and a transfer tank arranged in series and having the separated gas phase returned from the top of the settling tank to a point in the reactor near the top of the fluidized bed. Such alternative preferred product discharge system obviates the

need for a recompression line 64, 66, 68, as shown in the system of the drawing.

The fluidized-bed reactor is equipped with an adequate venting system (not shown) to allow venting the bed during start up and shut down. The reactor does not require the use of stirring and/or wall scraping. The recycle line 22 and the elements therein (compressor 30, heat exchanger 24) should be smooth surfaced and devoid of unnecessary obstructions so as not to impede the flow of recycle fluid or entrained particles.

Among the polymers which may be produced in the process of the present invention are homopolymers of ethylene, propylene, butene or copolymers of a major mole percent of ethylene, propylene or butene and a minor mole percent of one or more C_2 to C_8 alpha-olefins. The C_2 to C_8 alpha-olefins preferably should not contain any branching on any of their carbon atoms which is closer than the fourth carbon atom. The preferred C_2 to C_8 alpha-olefins are ethylene, propylene, butene-1, pentene-1, hexene-1, 4-methylpentene-1 and octene-1.

The ethylene polymers, for example, have a melt flow ratio of over about 22. The melt flow ratio value is another means of indicating the molecular weight distribution of a polymer. A melt flow ratio (MFR) of 22 thus, for example, corresponds to a M_w/M_n value (as determined by conventional size exclusion chromatography) of about 2.7.

The ethylene homopolymers have a density of about 0.958 to 0.972 g/cm³.

The ethylene copolymers have a density less than about 0.96 g/cm³. The density of the ethylene copolymer, at a given melt index level for the copolymer, is primarily regulated by the amount of the C_3 to C_8 comonomer which is copolymerized with the ethylene. In the absence of the comonomer, the ethylene would homopolymerize to provide

polymers having a density of about ≤ 0.96 . Thus, the addition of progressively larger amounts of the comonomers to the copolymers results in a progressive lowering of the density of the copolymer. The amount of each of the various C_3 to C_8 comonomers needed to achieve the same result will vary from monomer to monomer, under the same reaction conditions.

Thus, to produce binary copolymers of ethylene with the same density and melt index, larger molar amounts of the different comonomers would be needed in the order of $C_3 > C_4 > C_5 > C_6 > C_7 > C_8$.

When made in the fluid-bed process described herein, ethylene polymers are granular materials which have a settled bulk density of about 0.24 to 0.51 g/cm³ (15 to 32 pounds per cubic foot) and an average particle size of the order of about 0.13 (0.005) to about 1.52 mm (0.06 inches). Particle size is important for the purposes of readily fluidizing the polymer particles in the fluid-bed reactor, as herein described.

In accordance with the present invention, a process is provided for increasing the space time yield of polymer production in a fluidized bed reactor employing an exothermic polymerization reaction ^{preferably} by cooling the recycle stream to below its dew point and returning the resultant two-phase fluid stream to the reactor to maintain the fluidized bed at a desired temperature above the dew point of the recycle stream. The cooling capacity of the recycle stream is increased both due to the greater temperature differential between the entering recycle stream and the reactor and by the vaporization of the condensed liquids entrained in the recycle stream.

It has, therefore, been found that the dew point limitation on the recycle stream broadly held heretofore by those skilled in the art, as pointed out hereinabove, has been unduly limiting and restricting. It has been found that such limitations are erroneous and need not to be practiced.

The amount of condensation, and thus the increase in production rate, can be further enhanced by altering the process conditions so as to increase the dewpoint of the recycle stream. It has been found that the amount of condensation of liquid in the recycle stream can be maintained at up to about 20 percent by weight, preferably up to about 10 percent. This degree of condensation is achieved by maintaining the outlet temperature from the cycle heat exchange zone so as to effect the required degree of cooling below the dew point of the mixture.

EXAMPLE 1

In an example of the process of the invention, a fluidized bed gas phase reaction system, as described above was operated with a partially condensed recycle stream to produce an hexene-1/propylene/ethylene copolymer, under the following conditions:

Recycle Stream Composition (mole percent):

Nitrogen	-	34.7
Ethylene	-	38.1
Ethane	-	8.9
Propylene	-	5.1
Hexene-1	-	4.8
Hydrogen	-	7.3
Methane	-	0.1

Recycle Stream Dewpoint: 57.8°C (at the pressure of the heat exchanger)

Reactor Gas Inlet Temperature: 48°C

Liquid in Cycle Gas: 4.6 wt. percent

Catalyst: a complex of tetrahydrofuran, magnesium chloride and titanium chloride reduced with diethyl aluminum chloride (diethyl aluminum chloride-to-tetrahydrofuran molar ratio of 0.4) and tri-n-hexyl aluminum (tri-n-hexyl aluminium-to-

tetrahydrofuran molar ratio of 0.4) impregnated on triethyl aluminum treated silica dioxide.

Reactor Temperature: 88°C

Reactor Pressure: 1963 kPa (270 psig)

Superficial Gas Velocity in the Fluidized Bed: 0.61 m/s
(2.0 feet/sec)

Bed Height: 11.3 m (37 feet)

Bed Diameter: 2.4 m (8 feet)

Space Time Yield: 81.7 kg/m³h (5.1 lb/ft³h)

Melt Index of Resin: 1.0 dg/min

Density of Resin: 0.918 g/cm³

Activator: triethyl aluminum

EXAMPLE 1a

The following example was carried out under essentially identical operating conditions as Example 1, differing only with respect to the cooling of the recycle stream and the rate of catalyst injection.

Recycle Stream Composition (mole percent):

Nitrogen - 36.5

Ethylene - 38.2

Ethane - 11.2

Propylene - 5.0

Hexene-1 - 4.1

Hydrogen - 4.8

Methane - None detected

Recycle Stream Dew Point: 53.2°C (at the pressure of the heat exchanger)

Reactor Gas Inlet Temperature: 60.6°C

Liquid in Cycle Gas: Zero

Reactor Temperature: 87.1°C

Reactor Pressure: 1963 kPa (270 psig)

Superficial Gas Velocity in the Fluidized Bed: 0.61 m/s
(2.0 ft/sec)

Bed Height: 11.3 m (37 feet)
Bed Diameter: 2.4 m (8 feet)
Space Time Yield: 32 kg/m³h (2.0 lb/ft³hr)
Melt Index of Resin: 1.0 dg/min
Density of Resin: 0.918 g/cm³
Activator: triethyl aluminum

It is to be noted that operation below the dew point of the recycle stream, as in Example 1, resulted in an increase in space time yield (pounds of resin produced per cubic foot of bed per hour) which was approximately 2.5 times those obtained without the employment of the liquid phase in the recycle stream, as in this Example 1a.

EXAMPLE 2

In another Example, employing butene-1 rather than propylene and hexene-1 as the other alpha-olefin monomer, the following conditions were maintained:

Recycle Stream Composition (mole percent)

Hydrogen - 6.3
Ethylene - 57.8
Butene-1 - 26.7
Inerts - 9.2

Recycle Stream Dewpoint: 49.7°C (at the pressure of the heat exchanger)

Reactor Gas Inlet Temperature: 47.2°C

Liquid in Cycle Gas: 1.2 wt. percent

Catalyst: a complex of tetrahydrofuran, magnesium chloride and titanium chloride reduced with tri-n-hexyl aluminum only (tri-n-hexyl aluminum-to-tetrahydrofuran molar ratio of 0.7) impregnated on tri-ethyl aluminum treated silica dioxide.

Reactor Temperature: 87.5°C

Reactor Pressure: 1956 kPa (269 psig)

Superficial Gas Velocity in the Fluidized Bed: 0.61 m/s
(2.0 ft/sec)

Bed Height: 11.3 m (37 feet)

Bed Diameter: 24 m (8 feet)

Space Time Yield: 99 kg/m³h (6.2 lb/ft³hr)

Melt Index of Resin: 1.0 dg/min

Density of Resin: 0.918 g/cm³

Activator: triethyl aluminum

EXAMPLE 2a

The following example was conducted under conditions similar to those employed in example 2 but without condensed liquid in the recycle gas stream.

Recycle Stream Composition (mole percent):

Hydrogen - 4.5

Ethylene - 59.3

Butene-1 - 26.7

Inerts - 9.5

Recycle Stream Dew Point: 44.1°C (at the pressure of the heat exchanged)

Reactor Gas Inlet Temperature: 56°C

Liquid in Cycle Gas: Zero

Catalyst: A complex of tetrahydrofuran, magnesium chloride and titanium chloride reduced with tri-n-hexyl aluminum only (tri-n-hexyl aluminum-to-tetrahydrofuran molar ratio of 0.7) impregnated on tri-ethyl aluminum treated silica dioxide.

Reactor Temperature: 83.7°C.

Reactor Pressure: 1928 kPa (265 psig)

Superficial Gas Velocity in the Fluidized Bed: 0.65 m/s
(2.14 ft/sec)

Bed Height: 11.4 m (37.5 feet)

Bed Diameter: 2.4 m (8 feet)
Space Time Yield: 59 kg/m³h (3.7 lb/ft³hr)
Melt Index of Resin: 1.0 dg/min
Density of Resin: 0.918 g/cm³
Activator: triethyl aluminum

EXAMPLES 3-8

The six following examples in tabular form set forth further information for practicing the process of the invention employing various condensing recycle streams for enhanced cooling of the fluidized bed in the polymerization of hexene-1/butene-1/ethylene, ethylene/propylene, ethylene/butene-1, pentene-1/ethylene, as well as the use of iso-pentane as an inert fluid in the polymerization of butene-1/ethylene and ethylene, respectively.

0241947

<u>Example No.</u>	<u>3</u>	<u>4</u>	<u>5</u>
Product	C ₆ /C ₄ /C ₂ Copolymer	C ₂ /C ₃ Copolymer	C ₂ /C ₄ Copolymer
Recycle Stream Composition (mole percent):			
Nitrogen	34.7	17.4	43.5
Ethylene	38.1	0.64	0.25
Ethane	8.9	-	-
Propylene	-	63.5	-
Propane	-	16.5	-
Butene-1	5.1	-	50.0
Butane	-	-	5.0
Pentene-1	-	-	-
Isopentane	1.0	1.0	0.5
Hexene-1	4.8	-	-
Hydrogen	7.3	0.95	0.75
Methane	0.1	-	-
Recycle Stream Dewpoint (°C)*	63.0	44.4	44.0
Reactor Inlet Temperature (°C)	54.3	43.5	41.6
Liquid in Cycle Gas (wt. percent)	4.8	4.2	8.8
Reactor Temperature (°C)	88	60	50
Reactor (kPa) Pressure ((psig))	1963 (270)	1963 (270)	935 (121)
Superficial Gas Velocity in Fluidized Bed (m/s) (ft/sec)	0.61 (2.0)	0.52 (1.7)	0.61 (2.0)
Bed Height (m) (feet)	11.3 (37)	11.3 (37)	11.3 (37)
Space Time Yield (kg/m ³ h) (lb/ft ³ hr.))	88 (5.5)	106 (6.6)	64 (4.0)

*At the pressure of the heat exchanger

0241947

Example No.	<u>6</u>	<u>7</u>	<u>8</u>
Product	C ₅ /C ₂ Copolymer	C ₄ /C ₂ Copolymer	C ₂ Homopolymer
Recycle Stream Composition (mole percent):			
Nitrogen	40.7	15.7	37.5
Ethylene	35.0	38.6	35.0
Ethane	9.0	3.0	5.0
Propylene	-	-	-
Propane	-	-	-
Butene-1	-	17.7	-
Butane	-	2.3	-
Pentene-1	10.5	-	-
Isopentane	-	14.2	10.5
Hexene-1	-	-	-
Hydrogen	3.8	6.2	11.0
Methane	1.0	2.3	1.0
Recycle Stream Dewpoint (°C)*	53.7	74.4	47.4
Reactor Inlet Temperature (°C)	42.5	65.9	34.0
Liquid in Cycle Gas (wt. percent)	8.4	11.5	10.5
Reactor Temperature (°C)	88	88	110
Reactor (kPa) Pressure ((psig))	1963 (270)	1963 (270)	1963 (270)
Superficial Gas Velocity in Fluidized Bed (m/s) ((ft/sec))	0.61 (2.0)	0.61 (2.0)	0.61 (2.0)
Bed Height (m) ((feet))	11.3 (37)	11.3 (37)	11.3 (37)
Space Time Yield (kg/m ³ h) ((lb/ft ³ hr.))	128 (8.0)	112 (7.0)	171 (10.7)

*At the pressure of the heat exchanger

The space time yield improvements achieved by the practice of this invention are the result of the increased cooling capacity of the recycle stream. This increased capacity is due both to the greater temperature differential between the entering recycle stream and the bed temperature and to the evaporation of condensed liquid entrained in the recycle stream.

It will be appreciated that increased cooling is achieved not only by evaporation of entering entrained liquid, but also by the overall reduction in the temperature of both the gas and liquid phases of the recycle stream in comparison to previously known methods of operation of fluidized bed reactor systems.

Although the process of the invention can be applied to increase the production rate from existing and new commercial reactors, the invention also has the potential of reducing equipment cost in new reactors. For example, plants designed according to the prior art for the production of certain ethylene copolymers made using hexene-1 as an other alpha olefin must have larger diameter reactors due to the lower space time yield. Since this invention increases the space time yield for products made with hexene-1 to that of conventional butene-1/ethylene copolymers, the extra cost associated with the larger diameter reactor can be eliminated by practicing the present invention. Alternately, the large diameter reactor can be retained and the velocity of the recycle stream reduced, resulting in lower capital and operating costs for the cycle gas compressor.

Advantages of this invention over other heat removal methods which use condensed liquids include the simplicity of this invention, good liquid distribution, maximum heat removal, and uniform gas stream composition in the polymerization zone as a result of introducing the two-phase recycle stream in the lower regions of the reactor. No liquid

collection, separation, or injection equipment is required and the liquids are dispersed in the stream entering the fluidized bed over the entire cross-sectional area, avoiding temperature gradients and high local concentrations of liquid around injection means.

CLAIMS:

1. A method for controlling the temperature of a fluidized bed during the production of polymers in a fluidized bed reactor by an exothermic polymerization reaction, which comprises continuously introducing into the bed a stream of gas cooled to below the maximum desired temperature within said bed and simultaneously or separately introducing a stream of liquid into said reactor under conditions such that an essentially uniform two-phase mixture of said gas and liquid is introduced in said bed at a level below the region of maximum desired temperature within said reactor.

2. A method according to claim 1 for controlling the temperature of a fluidized bed during the production of polymers in a fluidized bed reactor, by an exothermic polymerization reaction, which comprises continuously introducing into said bed an essentially uniform gas-liquid mixture containing monomer.

3. A process for producing polymers from one or more monomers by an exothermic polymerization reaction in a fluidized bed reactor having an upper polymerization zone containing a bed of growing polymer particles and a lower gas diffusion zone, which comprises:

- 1) continuously introducing a two-phase gas-liquid stream containing one or more monomers into said polymerization zone with an upward velocity sufficient to maintain said particles in a suspended and gas fluidized condition;
- 2) continuously introducing a polymerization catalyst into said polymerization zone;
- 3) continuously withdrawing polymer product from said polymerization zone; and
- 4) continuously withdrawing unreacted gases from the said polymerization zone, compressing and cooling said gases to a temperature below the dew point of said gases.

4. A process according to claim 3 wherein said two-phase mixture of gas and entrained liquid is introduced into said reactor at a point below the polymerization zone.

5. A process according to claim 3 wherein said unreacted fluids are compressed prior to cooling.

6. A process according to claim 3 wherein an inert condensible fluid is present in said two-phase mixture to raise the dew point of said mixture.

7. An improved process according to claim 6 wherein said inert condensible fluid is a saturated hydrocarbon.

8. A process according to claim 3 wherein the liquid phase of said two-phase mixture is less than about 20 percent by weight of the total weight of said two-phase mixture.

9. A process according to claim 3 wherein the liquid phase of said two-phase mixture is less than about 10 percent by weight of the total weight of said two-phase mixture.

10. A process according to claim 3 wherein the flow rate of said two phase mixture and the ratio of liquid to gas in said mixture are maintained at a level sufficient to maintain said liquid entrained in said gas until volatilized or until entry into said polymerization zone.

11. A process according to claim 3 wherein the gas stream flowing upwardly through said fluidized bed is essentially uniform in composition and moving in a manner through said bed such that the entire bed is maintained in a fluidized condition and with essentially no dead spaces through which gases do not pass.

12. A process according to claim 3 wherein additional quantities of one or more monomers in liquid or gaseous form are added to replace monomers polymerized and withdrawn as product, below the polymerization zone and at or near the point of entry of said two-phase mixture into said reactor.

13. A process according to claim 3 wherein additional quantities of one or more monomers are added to replace monomers polymerized and withdrawn as product by injection into the gas-liquid stream prior to entry of the said two-phase mixture into the reactor.

14. A process according to claim 3 wherein gas distributor means is provided immediately below said polymerization zone.

15. A process according to claim 3 wherein the internal pressure within said reactor is from about 100 psi to about 350 psi.

16. A process according to claim 3 wherein said polymer is produced by reaction of an alpha olefin monomer having from two to four carbon atoms alone or in admixture with one or more other alpha olefin monomers having from two to eight carbon atoms.

